

ORTON/RRC Test Report
ASTM C24 Pyrometric Cone Equivalent (PCE)

Engineer: JH
Technician: KK

Customer: WHITACRE GREER
Customer PO: VERBAL
Report Date: 03/16/2007

	Sample Info.	PCE Value	Deformation Temp., F	Comments
Brand Grade Lot	ST. LINE	19 - 20	2806 - 2847	
Brand Grade Lot	KIMBLE	16 - 17	2716 - 2754	
Brand Grade Lot	MIX	17 - 18	2754 - 2772	